



VENETAIMBALLAGGI

PROTEGGE I TUOI PRODOTTI

LLDPE cast stretch film mechanically pre-stretched to very low thickness. Specially indicated where there are light and/or easily deformable goods. Slippery outside and cling inside.

To be used only on wrapping machines WITHOUT prestretch group or for manual use.

| Characteristic | Method | Unit | Direction | 6 µm | 7 µm | 8 µm | 9 µm | 10 µm | Tolerances |
|---------------------------|--------------|------|-----------------------|------|------|------|------|-------|------------|
| Impact resistance | ASTM D1709 A | g | - | 35 | 39 | 41 | 44 | 47 | 10% |
| Tensile strength at break | ASTM D882 B | MPa | Machine Direction | 74 | 75 | 76 | 76 | 77 | 10% |
| | | | Transversal Direction | 19 | 20 | 20 | 21 | 21 | 10% |
| Tensile strength at yield | ASTM D882 B | MPa | Machine Direction | 38 | 38 | 38 | 39 | 40 | 10% |
| | | | Transversal Direction | 5 | 5 | 5 | 5,5 | 5,5 | 10% |
| Elongation at break | ASTM D882 B | % | Machine Direction | 120 | 130 | 135 | 140 | 145 | 10% |
| | | | Transversal Direction | 735 | 750 | 800 | 825 | 850 | 10% |
| Tear Resistance | ASTM D1922 | mN | Machine Direction | 980 | 1010 | 1030 | 1045 | 1060 | 10% |
| | | | Transversal Direction | 2400 | 2410 | 2450 | 2480 | 2550 | 10% |
| Stretch | Hipac | % | - | 10 | 10 | 15 | 20 | 25 | 5% |
| Cling | Hipac | g | - | 125 | 125 | 125 | 125 | 125 | 10% |

| Coloured | AUV 6/12 months | Antistatic | NetRoll | Cling Out/In/Both | Printed |
|----------|-----------------|------------|---------|-------------------|---------|
| ✗ | ✗ | ✗ | ✓ | ✗ | ✗ |

Veneta Imballaggi S.r.l.

37050 - Villafontana di Oppeano (Vr) - Via Villafontana, 291

T. +39 045 714 5181 / F. +39 045 698 9047

info@venetaimballaggi.eu - www.venetaimballaggi.eu